

GENERAL PRODUCT SPECIFICATION

Item No. AW412

Date 16-6-2017 Replaces 6-1-2016 No. Pages 1

Product Description:

Style SOC

Item Size (each)7.6 cm d x 122 cm longColorGray with black logo printing

Composition Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 %

Structure Sorbent fill: Micro-fibrous meltblown polypropylene (2-10 micron diameters)

Outer covering: Spunbond polypropylene nonwoven (15-30 micron dia. fiber)

Technology Meltblown + Spunbond + Sealed or Enclosed Ends

Absorbency Hydrophilic + Oleophilic

Intended Application Chemical Resistant "Universal" Sorbent Sock for Spills of Water Base, Oil

Base, or Solvent Base Liquids

Absorbency Capacity 43 l per case (saturated; medium viscosity- 9x)

Packaging Description:

tronger g = to tronger								
Package configuration	Case	Pkg. Weight		4.7 kg (4.1kg)				
Items per Package	12 SOCS/Case		Pkg. Dimensions (approx.)	57 cm x 32 cm				
				x 38 cm (H)				
Container type	Carton							

Physical Properties;

Parameter Parameter	SPC Test Method	<u>Units</u>	<u>Nominal</u>	(+/-)Tolerance
SOC Weight	Gravimetric	kg	0.36	0.09
Absorbency ** (med.	SPCTM-012B	gL/gS	9	8-min.
oil)				

oil)

Color Visual ----- Gray per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes Product will be free of foreign material contamination, rips, holes, and tears. **Labeling** Each package to be clearly labeled with Company Name, Address, Item No.,

Date, and/or Package Code (Bar Code).

Certification Make no changes in basic process or composition without notifying customer.

Claims for non-conformance of goods must be made within 60-days of delivery.