



GENERAL PRODUCT SPECIFICATION

| | |
|-----------------|------------------|
| Item No. | GP152-P-E |
|-----------------|------------------|

| | | | | | |
|-------------|----------|-----------------|-----------|------------------|---|
| Date | 3-3-2022 | Replaces | 16-6-2017 | No. Pages | 1 |
|-------------|----------|-----------------|-----------|------------------|---|

Product Description:

| | |
|-------------------------|---|
| Style | Blanket roll, high strength perforation every 44 cm for single or multiple/variable length pads |
| Item Size (each) | 48 cm wide by 44 m long (100 Pads) |
| Color | Gray |
| Composition | Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 % |
| Structure | A nonwoven mat of randomly oriented Micro-fibers [2-10 micron diameters] |
| Technology | Meltblown |
| Absorbency | Universal (Hydrophilic + Oleophilic) |
| Bonding | Bonded (staggered pattern) + Mechanical entanglement |

| | |
|-----------------------------|--|
| Intended Application | Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids |
|-----------------------------|--|

| | |
|----------------------------|--|
| Absorbency Capacity | 192 l per bale (saturated; medium viscosity-14x) |
|----------------------------|--|

Packaging Description:

| | | | |
|-----------------------|---------------------|-----------------|------------------------|
| Package configuration | Bale | Pkg. Weight | 12.0 kg (11.8kg) |
| Items per Package | 2 Blanket Roll/Bale | Pkg. Dimensions | 43cm x 43cm x 98cm (H) |
| Container type | Polybag + Twist tie | | |

Physical Properties:

| <u>Parameter</u> | <u>SPC Test Method</u> | <u>Units</u> | <u>Nominal</u> | <u>(+/-)Tolerance</u> |
|--------------------------|------------------------|--------------|----------------|-----------------------|
| Basis Weight | SPCTM-002A | G/M2 | 280 | 28 |
| Caliper | SPCTM-020 | mm | 4.6 | 0.4 |
| Absorbency ** (med. Oil) | SPCTM-004B | gL/gS | 14 | 2 |
| Tensile strength | SPCTM-007 | daN | 6.3 | 0.6 |
| Color | Visual | ----- | Gray | per standard |

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

| | |
|----------------------|--|
| Attributes | Product will be free of foreign material contamination, rips, holes, and tears. |
| Labeling | Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code). |
| Certification | Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery. |