



GENERAL PRODUCT SPECIFICATION

Item No.	HT777-E
-----------------	----------------

Date	16-6-2017	Replaces	4-11-11	No. Pages	1
-------------	-----------	-----------------	---------	------------------	---

Product Description:

Style	Perforated Blanket Roll; perforated lengthwise for the (4) 19 cm width dimensions, & then perforated cross-wise every 38 cm for length dimension.
Item Size (each)	76 cm wide by 46 m long (480 pads per roll)
Color	Gray
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 %
Structure	A trilaminate nonwoven mat of randomly oriented micro-fibers [2-10 micron diameters] contained within outer coverstocks. One coverstock is a gray lint-resistant & abrasion resistant spunbond nonwoven of continuous filaments, randomly oriented and thermally point bonded [15-30 micron diameters]; the other coverstock is a lint-resistant gray meltblown nonwoven. The (3) plies are secured together with bonded dimpling.
Technology	Meltblown, Spunbond
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Abrasion Resistant, Lint Resistant, & Chemical Resistant Universal Sorbent for Water-Based, Oil or Solvent Base Liquids- for single or various sized pad
-----------------------------	---

Absorbency Capacity	185 l per bale (saturated; medium viscosity-12.5x)
----------------------------	--

Packaging Description:

Package configuration	Case	Pkg. Weight	14 kg (12.8 kg)
Items per Package	1-Roll / Case	Pkg. Dimensions	46 cm x 46 cm x 79 cm (H)
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	365	36
Caliper	SPCTM-003A	mm	5.2	0.5
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-006	daN	20	2
Color	Visual	-----	Gray	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.