



GENERAL PRODUCT SPECIFICATION

Item No.	SXT330-DP-E
-----------------	--------------------

Date	16-6-2017	Replaces	4-11-11	No. Pages	1
-------------	-----------	-----------------	---------	------------------	---

Product Description:

Style	Blanket Roll; high strength perforation every 46cm for single or multiple/variable length pads
Item Size (each)	76 cm x 46 m (200 pads)
Color	White
Composition	100% Polypropylene
Structure	A bonded trilaminate nonwoven mat wherein the middle white layer is randomly oriented meltblown micro-fibers [2-10 micron diameters], and the coverstock layers are lint-resistant & abrasion resistant {controlled porosity} spunbond nonwoven of continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters].
Technology	Spunbond & Meltblown (3-ply construction)
Absorbency	Hydrophobic + Oleophilic
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Abrasion Resistant, Lint Resistant, & Chemical Resistant Sorbent for Oil or Solvent Base Liquids
-----------------------------	--

Absorbency Capacity	141 l per Roll (saturated; medium viscosity-13.5x)
----------------------------	--

Packaging Description:

Package configuration	Case	Pkg. Weight	11.4 kg (10.1 kg)
Items per Package	1 Roll / Case 200 pads	Pkg. Dimensions	46 cm x 46 cm x 79 cm (H)
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002	G/M2	290	29
Caliper	SPCTM-003	mm	4.6	0.5
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12	2
Tensile Strength	SPCTM-007	daN	30	3
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information. Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use,

**SPC International, Atealaan 71, I.Z. Klein Gent, B-2200 Herentals, Belgium
Tel +32(0)14 321855 Fax +32(0)14 320440 www.bradyeurope.com**